

## Technical Data Sheet

# LASTENE 55-30B

## High Density Polyethylene

**HD55-30** is a Phillips Process Blow Molding copolymer certified prime grade designed to meet end-use requirements of containers for packaging of Household Industrial Chemicals (HIC). **HD55-30** features medium swell, easy and consistent processability in conventional continuous or intermittent extrusion equipment, and excellent balance of bottle ESCR, Impact strength and Stiffness. **HD55-30** recommended processing temperature is 160 to 180°C., with mold at 10 to 30°C. **HD55-30** complies with FDA regulation 21CFR 177.1520 (c) 3.1 (a) + 3.2 (a) and with most international regulations concerning the use of Polyethylene in contact with food articles.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
<b>PHYSICAL</b>			
Melt Flow Rate (190 °C, 2.16kg)	D1238	g/10 min	0.35
Density	D1505	g/cm <sup>3</sup>	0.954
HDT Under Load (66 psi Unannealed)	D648	°F	165
Environmental Stress-Cracking Resistance (122 °F, Compression, F50)	D1693	hr	50
<b>MECHANICAL</b>			
Flexural Modulus <sup>1</sup> - 1% Secant	D790	psi	195k
Tensile Strength @ Yield <sup>2</sup>	D638	psi	3900
Tensile Impact Strength	D1822	ft-lb/in <sup>2</sup>	98
Elongation @ Break <sup>2</sup>	D638	%	> 700

Typical Value of Properties not to be construed as specifications

\* Test Made on injection molded Type 1 tension test specimen according to ASTM D2146

1 - @ 0.051 in/min

2 - @ 2 in/min.



The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, Lastique International Corp.\* disclaims responsibility for reliance and results of use of this information. LASTIQUE INTERNATIONAL CORP. DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Lastique International Corp. expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.